

Vince Pitelka, 2015

Recipes for Stock ACC Cone-6 Glazes

Most of the glaze recipes below are given here as they were provided to us by Susan Demay.

**Rust Red**

Flint	2700
EPK	450
Potash Spar (g-200)	1800
Talc	1260
Red Iron Ox	1350
Bentonite	180
Gerstley Borate	2880

**Klinesville Gold**

Whiting	1669
Wollastonite	500
Neph Sye	4545
Red Art	1129
Red Iron Ox	590
Manganese Diox.	410
Zircopax	1039

**Keen Green**

Gerstley Borate	1360
Potash Spar	4600
Flint	1880
EPK	250
Whiting	810
Zircopax	600
Dolomite	600
Bentonite	100
Copper Carb	663
Rutile	250

**Light Yellow**

Potash Spar	3030
Flint	2010
Gerstley Borate	2010
EPK	1020
Dolomite	1000
Mason 6485 Yellow	510
Tin Oxide	300

**Tenmoku**

Potash Spar	3500
EPK	500
Flint	1900
Whiting	1500
Frit 3134	1200
Red Iron Ox	1000
Bentonite	160

**Pinnell Strontium**

Lithium Carb	100
Strontium Carb	2000
Neph Sye	6000
OM4 Ball Clay	1000
Flint	900
Titanium Dioxide	533
Copper Carb	500

**Floating Blue**

Neph Sye	47.3
Gerstley Borate	27
Flint	20.3
EPK	5.4
Red Iron Ox	2
Cobalt Oxide	1
Rutile (light)	4

**Ron Meyers Clear (08-9)**

Frit 3124	80
EPK	10
Flint	10
Epsom Salts	2%
Bentonite	2%

- To use as a liner add 10 Zircopax
- For Dipping, mix extremely thin, like dirty dish water or skim milk